

19
cited in the European Search
Report of EPC5 CC 3487.5
Your Ref.: 58575-3/4639



Europäisches Patentamt

⑯

European Patent Office

Office européen des brevets



⑪ Publication number: 0 583 940 A2

⑫

EUROPEAN PATENT APPLICATION

⑯ Application number: 93306340.6

⑮ Int. Cl.⁵: B41M 5/38

⑯ Date of filing: 11.08.93

⑯ Priority: 14.08.92 JP 239018/92
05.03.93 JP 44799/93
05.03.93 JP 44800/93
12.03.93 JP 52343/93

⑯ Date of publication of application:
23.02.94 Bulletin 94/08

⑯ Designated Contracting States:
DE FR GB

⑯ Applicant: TOYO INK MANUFACTURING CO., LTD.
3-13, Kyobashi 2-chome
Chuo-ku, Tokyo 104 (JP)

⑯ Inventor: Kimura, Yasunori, c/o Toyo Ink Mfg. Co., Ltd.
3-13, Kyobashi, 2-chome
Chuo-ku, Tokyo (JP)
Inventor: Yoshikawa, Takeshi, c/o Toyo Ink Mfg. Co., Ltd.
3-13, Kyobashi, 2-chome
Chuo-ku, Tokyo (JP)
Inventor: Kuwabara, Akifumi, c/o Toyo Ink Mfg. Co., Ltd.
3-13, Kyobashi, 2-chome
Chuo-ku, Tokyo (JP)
Inventor: Nakao, Tatsuya, c/o Toyo Ink Mfg. Co., Ltd.
3-13, Kyobashi, 2-chome
Chuo-ku, Tokyo (JP)
Inventor: Kashioka, Motohiko, c/o Toyo Ink Mfg. Co., Ltd.
3-13, Kyobashi, 2-chome
Chuo-ku, Tokyo (JP)

⑯ Representative: Myerscough, Philip Boyd
J.A. Kemp & Co. 14 South Square, Gray's Inn
London WC1R 5LX (GB)

⑯ Method of thermal transfer recording.

⑯ A thermal transfer recording method which comprises thermally transferring an image onto a marking film from a thermal transfer ribbon, wherein the marking film is a plastic film containing a heat adhesive resin or is a plastic film on which a heat-sensitive image-receiving layer composed mainly of a heat adhesive resin is formed and the thermal transfer ribbon is a laminate comprising a substrate and, in order on one surface of the substrate, a separable layer and a coloring ink layer consisting essentially of a resin and coloring material. The method permits the facile formation of fine or complicated, multi-color images on a marking film in quick operation at a low cost, and can give a recorded marking film having excellent weatherability, abrasion resistance and scratch resistance.

EP 0 583 940 A2

Jouve, 18, rue Saint-Denis, 75001 PARIS



EUROPEAN SEARCH REPORT

Application Number
EP 93 30 6340

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int.Cl.)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
X	EP-A-0 367 149 (DAI NIPPON PRINTING COMPANY LIMITED) * page 5, line 12 - line 19 * * page 5, line 45 - line 50 * * claims 1,4,13; examples 1-5 * ----	1-11	B41M5/38 B41M5/00 B41M5/40
A	EP-A-0 228 066 (EASTMAN KODAK COMPANY) * page 2, line 11 - line 18; claims 1-3 * -----	1-11	
			TECHNICAL FIELDS SEARCHED (Int.Cl.)
			B41M
The present search report has been drawn up for all claims			
Place of search	Date of completion of the search		Examiner
THE HAGUE	13 January 1995		Bacon, A
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			
T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

erties such as thermal transfer receiving properties, weatherability, etc., and patterning on said marking film with a thermal transfer ribbon.

SUMMARY OF THE INVENTION

5

It is an object of the present invention to provide a thermal transfer recording method which permits the facile formation of a fine or complicated, multi-color character or pattern on a marking film in quick operation at a low cost.

10

It is another object of the present invention to provide a thermal transfer recording method, which can give a recorded marking film having excellent weatherability, abrasion resistance and scratch resistance.

It is another object of the present invention to provide a thermal transfer recording method for the thermal transfer of a character or pattern to a marking film by means of a thermal transfer printer which permits facile maintenance and inspection.

15

According to the present invention, there is provided a thermal transfer recording method comprising patterning on a marking film which is a plastic film containing a heat adhesive resin or which is a plastic film on which a heat-sensitive image-receiving layer composed mainly of a heat adhesive resin is formed, with a thermal transfer ribbon prepared by consecutively laminating a separable layer and a coloring ink layer consisting essentially of a resin and a coloring material on one surface of a substrate.

20

DETAILED DESCRIPTION OF THE INVENTION

25

The thermal transfer recording method of the present invention is carried out using a thermal transfer ribbon prepared by forming a heat-melting ink layer on one surface of a substrate and a marking film which is a plastic film containing a heat adhesive resin or which is a plastic film on which a heat-sensitive image-receiving layer composed mainly of a heat adhesive resin is formed.

30

In a specific embodiment using a marking film having a heat-sensitive image-receiving layer, the heat-melting ink layer and the image-receiving layer are stacked one on the other, and in this state, the heat-melting ink layer forming a character or a pattern is melt-transferred to the image-receiving layer by applying a heating means such as a thermal head to that side of the thermal transfer ribbon which is not in contact with the heat-melting ink layer, whereby the character or pattern is directly formed on the surface of the marking film. That is, when a plastic film contains a heat adhesive resin which can be easily melted at a heat volume applied during the thermal transfer recording, or when a plastic film has on its surface an image-receiving layer formed of said heat adhesive resin, the thermal transfer ink and the marking film which are in contact are easily thermally melted in an interface, and allowed to adhere to each other, at a heat volume and a pressure applied during the thermal transfer recording, whereby character- or pattern-recorded film excellent in transfer properties and adhesion can be obtained.

35

The thermal transfer recording method of the present invention has the following advantages.

The present invention uses a thermal transfer printer which permits facile maintenance.

40

A desired image (i.e., a character or pattern) having a resolution depending upon the density of heat-generating elements of a thermal head can be obtained at a low cost immediately.

A multi-color image-recorded film can be obtained by carrying out transfer operations using thermal transfer ribbons which give different colors.

The thermal transfer recording method of the present invention can be used in combination with existing image forming means such as silk screen printing.

45

The marking film on which a character or pattern is recorded by thermal transfer can be cut to any desired forms.

That surface of the marking film which has a recorded character or pattern can be coated with a transparent plastic film.

50

The constituent members used in the thermal transfer recording method of the present invention will be explained hereinafter.

The marking film used in the present invention has a characteristic feature in that since it is a plastic film containing a heat adhesive resin or a plastic film having on the surface a thermal transfer image-receiving layer composed mainly of a heat adhesive resin, it has excellent thermal transfer receiving properties to a heat-melting ink, which conventional marking films do not have.

55

The plastic film used in the present invention is a film formed from at least one of a polyvinyl chloride resin, a polyester resin, a polyurethane resin, polyethylene, polypropylene, polystyrene, nylon, polyimide and a polyvinyl resin. Preferred is a film formed from a polyvinyl chloride resin, a polyester resin or a polyurethane resin. The plastic film preferably has a thickness of 30 to 500 μm . Particularly preferred is a polyvinyl chloride resin

film which has so high flexibility that it can be uniformly attached to a curved or roughened surface.

The polyvinyl chloride resin has a polymerization degree of 300 to 2,000, preferably 600 to 1,500, and includes a polyvinyl chloride resin alone and a resin obtained by the copolymerization of vinyl chloride and other monomer such as an olefin monomer, a diene monomer, a halogenated vinyl monomer, an acrylic ester monomer, a methacrylic ester monomer, a vinyl ester monomer or a styrene monomer. More specifically, the polyvinyl chloride resin includes an ethylene/vinyl chloride resin, a vinyl chloride/vinyl acetate resin, an ethylene/vinyl chloride/vinyl acetate resin and a urethane/vinyl chloride resin. In particular, a polyvinyl chloride resin having a softening point of 180°C or lower serves to improve the adhesion to a heat-melting ink. The plastic film used in the present invention may be a film formed from one of the above polyvinyl chloride resins or at least two of them in combination.

The plastic film may contain known additives such as a plasticizer, a coloring material, a heat stabilizer, an ultraviolet absorbent, an antistatic agent, an antioxidant and a lubricant.

The plasticizer includes a low-molecular-weight ester plasticizer formed from a carboxylic acid and a monovalent or polyvalent alcohol, a liquid polyester plasticizer, an alkyd liquid plasticizer and an oxirane oxygen-containing epoxy plasticizer. The carboxylic acid includes phthalic acid, isophthalic acid, tetrahydrophthalic acid, adipic acid, sebacic acid, maleic acid, fumaric acid, trimellitic acid and oleic acid.

The coloring material includes colored organic pigments and inorganic pigments conventionally used in printing inks. Further, a colorless or white extender pigment may be incorporated for improving the fluidity and imparting the anchoring effect of a heat-melting ink. A colored coloring material is preferred for obtaining a marking film having an aesthetically fine appearance, and a white coloring material is preferred for showing a character or pattern in good contrast.

The heat stabilizer includes calcium stearate, barium stearate, lead stearate, basic lead sulfite, dibasic lead phosphite, dibutyltin dimaleate, dibutyltin dilaurate, dibutyltin dimercaptide, diocetyltin dimaleate, diocetyltin dilaurate, diocetyltin dimercaptide, a tin diol derivative and a complex of these.

The ultraviolet absorbent is selected from compounds which absorb light having a wavelength of 290 to 400 nm. The ultraviolet absorbent includes benzophenone compounds, benzotriazole compounds, salicylic acid phenyl ester compounds, cyanoacrylate compounds, cinnamic acid compounds and aminobutadiene compounds. An ultraviolet light shielding agent may be used. The ultraviolet light shielding agent includes titanium oxide fine powder, zinc white, talc, kaolin, calcium carbonate and iron oxide.

The antistatic agent includes polyoxyethylenealkylamine, polyoxyalkylamide, polyoxyethylene alkyl ether, glycerin fatty acid ester, sorbitan fatty acid ester, alkyl sulfonate, alkylbenzene sulfonate, alkyl sulfate, alkyl phosphate and quaternary ammonium sulfate. The antistatic agent particularly serves to prevent the adhering of dust which would cause the occurrence of a white spot in a recorded character or pattern.

The lubricant includes hydrocarbon lubricants such as liquid paraffin and polyethylene wax, fatty acid lubricants such as stearic acid and oxyfatty acid, fatty acid amide lubricants, natural or synthetic ester wax and alcohol lubricants. The lubricant is used in such an amount that does not affect the thermal transfer. The lubricant improves the feeding of a marking film within a thermal transfer printer and the abrasion resistance of a marking film surface.

The heat adhesive resin includes a styrene/maleic anhydride copolymer, a styrene/acrylate copolymer, a styrene/methacrylate copolymer, polyvinyl acetate, a vinyl chloride/vinyl acetate copolymer, polyethylene, polypropylene, polyacetal, an ethylene/vinyl acetate copolymer, an ethylene/acrylate copolymer, an α -olefin/maleic anhydride copolymer, an esterification product of an α -olefin/maleic anhydride copolymer, polystyrene, polycaprolactone, polyacrylate, polymethacrylate, polyamide, an epoxy resin, a xylene resin, a ketone resin, a petroleum resin, sucrose ester, rosin or rosin derivatives, a coumarone-indene resin, a terpene resin, a polyurethane resin, synthetic rubbers such as styrene-butadiene rubber, polyvinyl butyral, nitrile rubber, acryl rubber and ethylene/propylene rubber, and a polyester resin.

Of the above heat adhesive resins, preferred are those which are hard solids or have no adhesion properties at room temperature. These resins generally have a glass transition temperature (to be referred to as Tg hereinafter) of -30 to 80°C or a softening or melting point of 40 to 180°C. Particularly preferred are those resins having Tg of -10 to 30°C and a softening or melting point of 50 to 150°C. A resin having Tg lower than the above lower limit and a softening or melting point lower than the above lower limit shows adhesion properties or fluidity at room temperature. As a result, a marking film undergoes a change with time, and it is liable to cause troubles such as blocking. Further, when a marking film is used outdoors, soot and smoke in atmosphere are adsorbed on the marking film surface to render it unclean. A resin having Tg higher than the above upper limit and a softening or melting point higher than the above upper limit is poor in heat sensitivity, and very poor in image transfer properties.

As the heat adhesive resin, particularly preferred are a highly crystalline or partially crystalline resin such as polycaprolactone of the formula of $-(CH_2CH_2CH_2CH_2CH_2COO)_n-$ (melting point, about 60°C), a crystalline

polyester resin, an epoxy resin and sucrose ester.

In particular, sucrose octabenoate (melting point 78°C) and sucrose octaacetate (melting point 72°C) satisfy the above requirements of hard solids and no adhesion properties at room temperature, and they have sharp melting points and low melting viscosity similar to that of wax and thus satisfy the heat sensitivity which is one of the important properties for thermal transfer. Further, sucrose octabenoate is remarkably suitable since it improves the weatherability. Sucrose octabenoate decreases the film strength to some extent when used alone, and it is therefore preferred to use sucrose octabenoate in combination with a resin which can give a film having high strength. The amount of sucrose octabenoate based on the total amount of heat adhesive resins is preferably 10 to 90 % by weight, more preferably 30 to 90 % by weight.

For improving the marking film in anti-blocking properties and soot and smoke resistance, it is preferred to use a fluorine-containing compound or a silicon-modified resin in combination with the above heat adhesive resin. The fluorine-containing compound includes a graft polymer in which acryl side chains bond to a main chain of a fluorine resin, fluorine-containing copolymer resins such as a copolymer obtained from a polyfluoro group-containing vinyl monomer and other vinyl monomer, a fluorine-containing surfactant and a fluorine-containing wax. The silicon-modified resin includes a resin in which polyorganosiloxane is introduced into a main chain or side chains. Above all, preferred are a silicon-modified polyurethane resin having a polyorganosiloxane chain in the main chain and a silicon-modified acrylic resin having a polyorganosiloxane chain in the side chains. The heat adhesive resin may be used in combination with other resin.

The marking film which is a plastic film containing the heat adhesive resin is produced by forming a resin composition containing 100 parts by weight of any resin described regarding the plastic film and 1 to 40 parts by weight of the heat adhesive resin into a film. The molding method includes an extrusion method, a calender method, a solution casting method, a sol casting method and a semi-sol casting method. Of these methods, particularly preferred are a sol casting method or a semi-sol casting method which do not involve hot roll processing in the formation of a film, since the resin composition contains the heat adhesive resin.

When the marking film is formed by a hot processing such as a calender method, the content of the heat adhesive resin in the plastic film is preferably 5 to 10 parts by weight for preventing the adhesion of the film to hot rolls or properly securing the film flexibility required when the marking film is used. When the marking film is produced by a casting method, the heat adhesive resin is required to be soluble in a solvent used, or a heat adhesive resin which is not at all soluble in a solvent cannot be used. In this case, a casting solution may contain a partially swollen undissolved resin. For example, a marking film which is a vinyl chloride copolymer film containing a heat adhesive resin is produced by a casting method as follows. The vinyl chloride copolymer resin, the heat adhesive resin, a plasticizer, a solvent and other optional component(s) are mixed and stirred to prepare a high-viscosity coating solution in a paste-like and sol-like state, and cast over a support sheet having film releasability such as a silicon-containing process paper sheet having film releasability or a stainless steel plate treated to have film releasability. Then, the high-viscosity coating solution is melted by heating it at 160 to 220°C for approximately 1 to 10 minutes, whereby the intended marking film having a thickness of 30 to 150 µm can be obtained. The solvent is selected from organic solvents for a sol such as butanol, butyl acetate, acetic acid, ethylene glycol monomethyl ether, diisobutyl ketone, xylene, cyclohexanone, aromatic petroleum naphtha, solvent naphtha and trichlene. These solvents may be used alone or in combination.

The marking film which is a plastic film having on the surface a heat-sensitive image-receiving layer composed mainly of the heat adhesive resin can be produced by a solvent coating method in which a composition for forming an image-receiving layer is dissolved or dispersed in a solvent or water to prepare a coating solution and the coating solution is applied and then dried, or by a hot-melt coating method in which a composition for forming an image-receiving layer is melted under heat to form the layer. The thickness of the heat-sensitive image-receiving layer is preferably approximately 0.1 to 10 µm, more preferably approximately 0.2 to 2 µm.

The heat-sensitive image-receiving layer is composed mainly of the above heat adhesive resin, while it may contain the above additives such as a plasticizer, a coloring material, an ultraviolet absorbent and an antistatic agent.

For further improving the marking film in outdoor weatherability and soot and smoke resistance, the marking film may be produced by forming on a plastic film a highly-heat sensitive first image-receiving layer composed mainly of a heat adhesive resin having Tg of -30 to 30°C or a softening or melting point of 40 to 80°C and further forming thereon a second image-receiving layer excellent in weatherability and soot and smoke resistance which is mainly composed of a heat adhesive resin having Tg of 30 to 80°C or a softening or melting point of 80 to 180°C or which is composed of a resin mixture of the above heat adhesive resin with the above fluorine-containing compound or silicon-modified resin. In this case, the thickness of the second image-receiving layer is preferably as small as possible for preventing a decrease in transfer image receiving properties. That is, the above thickness is preferably 0.5 µm or less, more preferably 0.1 µm or less.

A character or pattern is transferred to one surface of the marking film from the thermal transfer ribbon.

The other surface of the marking film may be coated with an adhesive such as an acrylic adhesive, a urethane adhesive, a rubber adhesive or a silicon adhesive in a coating thickness of 10 to 200 μm and then with a separable sheet. The adhesive is generally selected from those having an adhesion strength of 1,000 to 2,000 gr/25 mm width (JIS-Z0237, adhesive tape adhesive sheet test method) depending upon the material and surface state of a surface to which the marking film is to be attached. Further, the adhesive may be selected from those adhesives having an adhesion strength of 50 to 1,000 gr/25 mm width, preferably 500 to 900 gr/25 mm width. In this case, the marking film can be peeled off without any residual adhesive on the surface to which the marking film has been attached and without any peel strength exceeding the breaking strength of the marking film.

10 The thermal transfer ribbon used in the present invention has a heat-melting ink layer formed by consecutively laminating a separable layer and a coloring ink layer on a substrate. The coloring layer substantially does not contain waxes which affect the weatherability, adhesion and abrasion resistance. For further improving the adhesion, an adhesive layer may be formed on the coloring ink layer.

15 The substrate used in the thermal transfer ribbon includes a polyester film excellent in heat resistance and mechanical strength (e.g., polyethylene terephthalate and polybutylene terephthalate), a polyolefin film (e.g., polypropylene), a polyamide film (e.g., nylon), a cellulose film (e.g., triacetate) and a polycarbonate film. A polyester film is particularly preferred, since it is excellent in heat resistance, mechanical strength, tensile strength and tensile stability. The smaller the thickness of the substrate is, the higher the thermal conductivity is. In view of strength and easiness in forming the heat-melting ink layer, the thickness of the substrate is most preferably approximately 3 to 50 μm . The heat-melting ink layer is formed on one surface of the substrate. The other surface of the substrate may be provided with a back coating formed of a heat-resistant resin.

20 The heat-melting ink layer is formed from coloring materials such as an organic pigment and an inorganic pigment and a vehicle. The vehicle includes natural waxes such as plant-derived wax, animal-derived wax, mineral-derived wax and petroleum-derived wax, synthetic wax, higher fatty acid, higher fatty acid derivative and a resin having a softening point of 200°C or lower.

25 In the present invention, the marking film is imparted with heat-sensitive image receiving properties, and there is used the thermal transfer ribbon obtained by forming a separable layer on a substrate and then forming a coloring ink layer consisting essentially of a coloring material and a resin but containing no wax on the separable layer. Therefore, a recorded portion in the marking film has excellent surface strength and adhesion. 30 A wax contained in the coloring ink layer serves to improve the heat sensitivity during the transfer. However, the marking film having a character or pattern recorded thereon shows a decrease in durability, particularly scratch resistance and adhesion, in a high-temperature environment (around 40°C). When the coloring ink contains about 5 % by weight of a wax, the marking film having a recording shows a decrease to some extent in the above properties as compared with a case where no wax is contained. When the coloring ink contains about 35 20 % by weight of a wax, the above properties clearly deteriorate, and in particular, the scratch resistance greatly deteriorates. When the coloring ink contains 50 % or more of a wax, the above properties deteriorates by 50 percent or more. The heat sensitivity decreases when the coloring ink layer contains no wax. However, this decrease in heat sensitivity can be fully compensated by the thermal transfer image receiving properties of the marking film.

40 The coloring material/resin weight ratio of the coloring ink layer specially has an influence on the undercolor concealing performance, color density and resolution. When the coloring material is an organic pigment, the above ratio is preferably 0.5 to 4. When the coloring material is an inorganic pigment, the above ratio is preferably 0.5 to 6 since inorganic pigments have greater specific gravity. When the above weight ratio is smaller than the above range, the concealing performance, i.e., the color density decreases, and the coloring ink layer shows too high film strength to obtain sharpness during the transfer. That is, the resolution decreases. When the above weight ratio is greater than the above range, the adhesion and abrasion resistance decrease. The coloring ink layer may contain known additives in an amount of 5 % by weight or less based on the total amount of solid contents as required. The thickness of the coloring ink layer is preferably 0.3 to 5 μm , more preferably 0.5 to 3 μm .

45 50 The releasing layer is composed from a wax and a resin, while the separable layer may further contain known additives such as a coloring material, a pigment dispersant, an antistatic agent, a plasticizer and an ultraviolet absorbent as required. The thickness of the releasing layer influences the transferring performance, and it is preferably 0.1 to 3 μm , more preferably 0.3 to 2 μm .

55 The resin used in the heat-melting ink layer is selected from those having a softening point of 200°C or lower, such as polyvinyl acetate, a vinyl chloride/vinyl acetate copolymer, polyethylene, polypropylene, polyacetal, an ethylene/vinyl acetate copolymer, an ethylene/acrylate copolymer, an α -olefin/maleic anhydride copolymer, an esterification product of an α -olefin/maleic anhydride copolymer, polystyrene, polyacrylate, polymethacrylate, an α -olefin/maleic anhydride/vinyl group-containing monomer copolymer, a styrene/maleic an-

hydride copolymer, a styrene/acrylate copolymer, polyamide, an epoxy resin, a xylene resin, a ketone resin, a petroleum resin, rosin or rosin derivatives, a coumarone-indene resin, a terpene resin, a polyurethane resin, synthetic rubbers such as styrene-butadiene rubber, polyvinyl butyral, nitrile rubber, acryl rubber and ethylene/propylene rubber, a polyester resin, nitrocellulose, cellulose derivatives, sucrose esters. Above all, preferred are a resin obtained by copolymerizing an α -olefin having at least 6 carbon atoms, maleic anhydride and (meth)acrylate, sucrose octabenoate (included in sucrose esters) and sucrose octaacetate (included in sucrose esters) in view of their heat sensitivity.

When an adhesive layer is laminated on a coloring ink layer, preferred are a resin, as a main component of the adhesive layer, obtained by copolymerizing at least one compound selected from the group of α -olefin having at least 6 carbon atom, maleic anhydride and (meth)acrylate for improving the adhesion and transfer properties.

The heat-melting ink layer can be formed by any known method such as a hot melt coating method or, preferably, a gravure coating method.

According to the present invention, highly vivid and accurate images including characters and patterns can be formed on the marking film containing the heat adhesive resin having heat-melting ink receiving properties, or on the marking film having the heat-sensitive image-receiving layer, in a facile operation. Therefore, the pattern processing can be easily carried out with immediate productivity at a low cost without carrying out complicated steps. Further, a marking film on which images including characters and patterns have been recorded can be fully practically used, since it retains flexibility, surface smoothness, dimensional stability and weatherability which are all required for practical use of marking films and since the heat-melting ink shows excellent adhesion.

The present invention will be explained more in detail hereinafter. In Examples, "part" stands for "part by weight".

25 Preparation Example 1 - Marking film A

The raw materials for a marking film A and their amounts were as shown below.

- Film -		
30	Titanium oxide pigment (TIPAQUE CR80, supplied by Ishihara Sangyo Kaisha, Ltd.)	30 parts
	Liquid polyester plasticizer (ADEKACIZER PN260, supplied by Asahi Denka Kogyo K.K.)	20 parts
35	Liquid phthalic acid ester plasticizer (DOP, supplied by Chisso Corp.)	15 parts
	Heat-bonding resin (JONCRYL 611, styrene-acrylic resin, softening point 105°C, supplied by Johnson Polymer Corp.)	20 parts
	Heat stabilizer (BZ100C, supplied by Katsuta Kako K.K.)	3 parts
40	Ultraviolet absorbent (TINUVIN 326, supplied by Ciba Geigy)	2 parts
	Solvent (xylene/diisobutyl ketone = 1/1)	284 parts
45	Vinyl chloride resin (ZEON 24, polymerization degree 1,300, supplied by Nippon Zeon Co., Ltd.)	100 parts
	Lubricant (stearyl alcohol)	1 part

- Adhesive -		
50	Acrylic pressure-sensitive adhesive (ORIBAIN BPS4089B, supplied by Toyo Ink Mfg. Co., Ltd.)	100 parts
	Isocyanate hardener agent (ORIBAIN BHS4089B, supplied by Toyo Ink Mfg. Co., Ltd.)	0.87 part

55 The titanium oxide pigment and the plasticizers were preliminarily mixed, and the mixture was fully kneaded with a three-roll mill to prepare a coloring paste. Then, heat adhesive resin, the heat stabilizer, the ultraviolet absorbent and the lubricant were dissolved in the solvent to prepare a resin solution. The vinyl chloride resin

5 powder and the above-prepared paste were added to the resin solution such that the total solid content was about 60 %, and the mixture was fully stirred with a mixer with cooling to give a sol paste. The sol paste was fully defoamed and applied to a separable paper sheet with an applicator such that the dry coating thickness was about 100 μm , and the applied paste was fully dried with hot air to give a resin film.

10 Separately, there was prepared a releasable paper sheet which had been formed by coating both surfaces of a 100 μm thick paper sheet with polyethylene and treating one surface of the resultant polyethylene-laminated film with a releasing agent. An adhesive obtained by fully mixing and stirring the above raw materials for an adhesive was applied to the releasable paper sheet such that the dry weight was 25 gr/m², and dried at 100°C for 2 minutes. This adhesive had an initial adhesion strength of 1,200 gr/25 mm width (JIS-Z0237, adhesive tape-adhesive sheet test method), and after it was allowed to stand at 65°C at 80 % RH for 168 hours, it showed an adhesion strength of 1,500 gr/25 mm width. This adhesive-applied releasable paper sheet and the above-prepared resin film were laminated to give the intended adhesive-applied marking film A. Then, the separable paper sheet was taken off.

15 Preparation Example 2 - Marking film B

20 An adhesive-applied marking film B was obtained in the same manner as in Preparation Example 1 except that the heat adhesive resin "JONCRYL 611" was replaced with sucrose octabenoate (MONOPET SB, melting point 78°C, supplied by Daiichi Kogyo Seiyaku Co., Ltd.).

25 Preparation Example 3 - Marking film C

The raw materials for a marking film C and their amounts were as shown below.

- Film -	
Titanium oxide pigment (TIPAQUE CR80, supplied by Ishihara Sangyo Kaisha, Ltd.)	30 parts
Vinyl chloride resin (ZEON 24, polymerization degree 1,300, supplied by Nippon Zeon Co., Ltd.)	100 parts
Heat-bonding resin (VYLYON 103, softening point 158°C, saturated polyester resin supplied by Toyobo Co., Ltd.)	20 parts
Liquid polyester plasticizer (ADEKACIZER PN260, supplied by Asahi Denka Kogyo K.K.)	20 parts
Liquid phthalic acid ester plasticizer (DOP, supplied by Chisso Corp.)	15 parts
Heat stabilizer (BZ100C, supplied by Katsuta Kako K.K.)	3 parts
Ultraviolet absorbent (TINUVIN 326, supplied by Ciba Geigy)	2 parts
Lubricant (stearyl alcohol)	1 part

- Adhesive -	
Acrylic pressure-sensitive adhesive (ORIBAIN BPS4294, supplied by Toyo Ink Mfg. Co., Ltd.)	100 parts
Isocyanate hardener agent (ORIBAIN BHS4089B, supplied by Toyo Ink Mfg. Co., Ltd.)	2 parts

50 The titanium oxide pigment and the plasticizers were preliminarily kneaded with a two-roll mill. Then, the heat adhesive resin, the heat stabilizer, the ultraviolet absorbent, the vinyl chloride resin and the lubricant were added to the above-kneaded mixture, and the mixture was fully kneaded while it was melted under heat. The resultant kneaded mixture was rolled under heat with a calender roll to give a resin film having a thickness of about 100 μm .

55 An adhesive obtained by fully mixing and stirring the above raw materials for an adhesive was applied to the same releasable paper sheet as that used in Preparation Example 1 such that the dry weight was 25 gr/m², and fully dried with hot air. This adhesive had releasability and had an initial adhesion strength of 500 gr/25 mm width (JIS-Z0237, adhesive tape adhesive sheet test method), and after it was allowed to stand at 65°C

at 80 % RH for 168 hours, it showed an adhesion strength of 750 gr/25 mm width. This adhesive-applied releasable paper sheet and the above-prepared resin film were laminated to give the intended adhesive-applied marking film C.

5 Preparation Example 4 - Marking film D

The raw materials for a marking film D and their amounts were as shown below.

- Film -		
10	Titanium oxide pigment (TIPAQUE CR80, supplied by Ishihara Sangyo Kaisha, Ltd.)	30 parts
15	Polyurethane resin (dicyclohexylmethane diisocyanate/polyhexamethylene carbonate diol (Mw 1,000)/propylene glycol/isophoronediamine = 4/1/1/1 (molar ratio))	100 parts
20	Heat-bonding resin (VYLON 103, softening point 158°C, saturated polyester resin supplied by Toyobo Co., Ltd.)	20 parts
	Ultraviolet absorbent (TINUVIN 326, supplied by Ciba Geigy)	2 parts
	Lubricant (stearyl alcohol)	1 part
	Solvent (cyclohexanone/diisobutyl ketone = 2/1)	400 parts

The above raw materials were fully dispersed and mixed in a ball mill to obtain a casting solution. The casting solution was applied to a separable paper sheet with an applicator such that the dry coating thickness was about 100 µm, and fully dried with hot air to give a resin film.

Preparation Example 5 - Marking film E

The raw materials for a marking film E and their amounts were as shown below.

- Image receiving layer -		
30	Heat-bonding resin (DESMOCOLL 530, softening point 85°C, polyurethane resin, supplied by Sumitomo Bayer Urethane Co., Ltd.)	10 parts
35	Ultraviolet absorbent (TINUVIN 326, supplied by Ciba Geigy)	2 parts
	Solvent (toluene/methyl isobutyl ketone = 5/1)	88 parts

The heat adhesive resin and the ultraviolet absorbent were fully dissolved in the solvent. The resultant solution was applied to a commercially available, 80 µm thick white polyurethane resin film such that the dry coating thickness was 0.5 µm, and fully dried with hot air to form a heat-sensitive image-receiving layer on the polyurethane resin film. Thereafter, the so-obtained film and the same adhesive-applied releasable paper sheet as that described in Preparation Example 3 were laminated to give an adhesive-applied Marking film E.

45 Preparation Example 6 - Marking film F

The raw materials for forming the image-receiving layer of a marking film F and their amounts were as shown below.

- Image receiving layer -		
50	Heat-bonding resin (VYLON 130, Tg 15°C, polyester resin, supplied by Toyobo Co., Ltd.)	5 parts
55	Heat-bonding resin (MONOPET SB, melting point 78°C, sucrose octabenoate, supplied by Daiichi Kogyo Seiyaku Co., Ltd.)	5 parts
	Solvent (toluene/methyl isobutyl ketone = 5/1)	90 parts

5 An adhesive-applied marking film F was obtained in the same manner as in Preparation Example 5 except that the white polyurethane resin film was replaced with a commercially available, 80 μm thick transparent vinyl chloride resin film and that the raw materials for an image receiving layer were changed as described above. The mixture of the above heat adhesive resins had Tg of 42°C.

10 Preparation Example 7 - Marking film G

The raw materials for forming an image receiving layer and their amounts were as shown below.

10	- Image receiving layer -	
	Heat-bonding resin (PLACCEL H7, melting point 60°C, polycaprolactone, supplied by Daicel Chemical Industries, Ltd.)	10 parts
15	Solvent (toluene/methyl isobutyl ketone = 5/1)	90 parts

20 The heat adhesive resin was completely dissolved in the solvent. The resultant solution was applied to a commercially available, 100 μm thick white polyethylene terephthalate (PET) film with a bar coater such that the dry coating thickness was 1 μm , and fully dried with hot air to form a heat-sensitive image-receiving layer, whereby a marking film G was obtained.

25 Preparation Example 8 - Marking film H

The raw materials for an image receiving layer and their amounts were as shown below.

25	- Image receiving layer -	
	Heat-bonding resin (VYLON 130, Tg 15°C, polyester resin, supplied by Toyobo Co., Ltd.)	12 parts
30	Fluorine-containing copolymer resin (FT-130, softening point 95°C, supplied by Asahi Glass Co., Ltd.)	3 parts
	Solvent (toluene/methyl ethyl ketone = 5/1)	85 parts

35 A marking film F was obtained in the same manner as in Preparation Example 7 except that the component for an image receiving layer was changed as described above. The mixture of the above heat adhesive resins had Tg of 18°C.

40 Preparation Example 9 - Marking film I

The raw materials for an image receiving layer and their amounts were as shown below.

40	- Image receiving layer -	
	Heat-bonding resin (VYLON 103, Tg 155°C, polyester resin, supplied by Toyobo Co., Ltd.)	8 parts
45	Silicon-modified urethane resin (DAIAROMER SP2105, softening point 95°C, supplied by Dainichiseika Colour & Chemicals Mfg. Co., Ltd.)	2 parts
	Solvent (toluene/methyl ethyl ketone = 1/1)	90 parts

50 An adhesive-applied marking film I was obtained in the same manner as in Example 5 except that the raw materials for an image receiving layer were changed as described above. The mixture of the heat adhesive resins had a softening point of 150°C.

55 Preparation Example 10 - Marking film J

The raw materials for an image receiving layer and their amounts were as shown below.

- Image receiving layer (1) -		
5	Heat-bonding resin (KEMIT R99, Tg -19°C, polyester resin, supplied by Toray Industries, Inc.)	15 parts
	Solvent (toluene/methyl ethyl ketone = 1/1)	85 parts
- Image receiving layer (2) -		
10	Heat-bonding resin (VYLON 103, Tg 155°C, polyester resin, supplied by Toyobo Co., Ltd.)	15 parts
	Solvent (toluene/methyl ethyl ketone = 1/1)	85 parts

15 The heat adhesive resin for an image receiving layer (1) was completely dissolved in the solvent, and the resultant solution was applied to a commercially available, 100 µm thick white vinyl chloride resin film with a bar coater such that the dry coating thickness was 0.5 µm, and fully dried with hot air to form a heat-sensitive image receiving layer (1). Then, the heat adhesive resin for an image receiving layer (2) was completely dissolved in the solvent, and the resultant solution was applied to the above-formed image receiving layer (1) with a bar coater such that the dry coating thickness was 0.1 µm, and fully dried with hot air to form a heat-sensitive image receiving layer (2). Then, the so-obtained film and the same adhesive-applied paper sheet as that obtained in Preparation Example 1 were laminated in the same manner as in Preparation Example 1 to give a marking film J.

Preparation Example 11 - Marking film K

25 The raw materials for an image receiving layer (2) and their amounts were as shown below.

- Image receiving layer (2) -		
30	Heat-bonding resin (VYLON 103, Tg 158°C, polyester resin, supplied by Toyobo Co., Ltd.)	10 parts
	Silicon-modified urethane resin (DAIAROMER SP2105, softening point 95°C, supplied by Dainichiseika Colour & Chemicals Mfg. Co., Ltd.)	5 parts
	Solvent (toluene/methyl ethyl ketone = 1/1)	85 parts

35 The same heat adhesive resin for an image receiving layer (1) as that used in Preparation Example 10 was completely dissolved in the same solvent as that used in Preparation Example 10, and the resultant solution was applied to a commercially available, 70 µm thick white polyurethane resin film with a bar coater such that the dry coating thickness was 0.5 µm, and fully dried with hot air to form a heat-sensitive image receiving layer (1). Then, the heat adhesive resin for an image receiving layer (2) was completely dissolved in the solvent, and the resultant solution was applied to the above-formed image receiving layer (1) with a bar coater such that the dry coating thickness was 0.1 µm, and fully dried with hot air to form a heat-sensitive image receiving layer (2), whereby a marking film K was obtained. The mixture of the resins for the heat-sensitive image receiving layer (2) had a softening point of 150°C.

45 Preparation Example 12 - Marking film L

The same adhesive processing as that in Preparation Example 1 was worked on a commercially available, 100 µm thick white vinyl chloride resin film to obtain a marking film L.

50 Preparation Example 13 - Thermal transfer ribbon 1

The raw materials for a separable layer and their amounts and the raw materials for a coloring ink layer and their amounts were as shown below.

5	- Separable layer -	
	Ethylene-vinyl acetate copolymer resin (EVAFLEX V577-2, supplied by Du Pont-Mitsui Polymers Co., Ltd.)	5 parts
10	Carnauba wax (Carnauba wax No. 1, supplied by Noda Wax)	20 parts
	Toluene	50 parts
	Isopropyl alcohol	25 parts

15	- Coloring ink layer -	
	Polyester resin (VYLON 200, supplied by Toyobo Co., Ltd.)	4 parts
20	Sucrose octabenoate (MONOPET SB, supplied by Diiichi Kogyo Seiyaku Co., Ltd.)	6 parts
	Carbon black	10 parts
	Dispersant	0.5 part
25	Toluene	40 parts
	Methyl ethyl ketone	40 parts

25 The raw materials for a separable layer were fully dispersed and mixed with a ball mill to prepare a coating solution. The coating solution was applied to one surface of a 4.5 µm thick polyethylene terephthalate film by a gravure coating method such that the dry coating thickness was 1 µm. The other surface of the polyethylene terephthalate film had a heat-resistant back coating. The raw materials for a coloring ink layer were fully dispersed and mixed with a sand mill to prepare a coating solution. The coating solution was applied to the separable layer by a gravure coating method such that the dry coating thickness was 1 µm to form a coloring ink layer, whereby a thermal transfer ribbon 1 was obtained.

30 **Preparation Example 14 - Thermal transfer ribbon 2**

35 The raw materials for a coloring ink layer and their amounts were as shown below.

40	- Coloring ink layer -	
	Polyester resin (VYLON 103, supplied by Toyobo Co., Ltd.)	10 parts
	Carbon black	10 parts
	Dispersant	0.5 part
45	Toluene	40 parts
	Methyl ethyl ketone	40 parts

50 A thermal transfer ribbon 2 was obtained in the same manner as in Preparation Example 13 except that the raw materials for a coloring ink layer were changed as described above.

55 **Preparation Example 15 - Thermal transfer ribbon 3**

The raw materials for a coloring ink layer and their amounts were as shown below.

- Coloring ink layer -	
5	Acrylic resin (DAIANAL BR112, supplied by Mitsubishi Rayon Co., Ltd.)
	7 parts
5	Sucrose octabenoate (MONOPET SB, supplied by Daichi Kogyo Seiyaku Co., Ltd.)
	3 parts
10	Carbon black
	10 parts
	Dispersant
	0.5 part
10	Toluene
	40 parts
	Methyl ethyl ketone
	40 parts

15 A thermal transfer ribbon 3 was obtained in the same manner as in Preparation Example 13 except that the raw materials for a coloring ink layer were changed as described above.

Preparation Example 16 - Thermal transfer ribbon 4

The raw materials for a coloring ink layer and their amounts were as shown below.

- Coloring in layer -	
20	α -Olefin/maleic anhydride/butyl methacrylate copolymer resin (molar ratio = 1/1/1, Mw = 50,000)
	10 parts
25	Carbon black
	8 parts
	Dispersant
	0.5 part
30	Methyl isobutyl ketone
	40 parts
	Methyl ethyl ketone
	40 parts

35 A thermal transfer ribbon 4 was obtained in the same manner as in Preparation Example 13 except that the raw materials for a coloring ink layer were changed as described above.

Preparation Example 17 - Thermal transfer ribbon 5

The raw materials for a coloring ink layer and their amounts were as shown below.

- Coloring ink layer -	
40	Polyester resin (KEMIT SQ1380, supplied by Toray Industries, Inc.)
	14 parts
	Carbon black
	6 parts
45	Dispersant
	0.1 part
	Toluene
	40 parts
	Methyl ethyl ketone
	40 parts

50 A thermal transfer ribbon 5 was obtained in the same manner as in Preparation Example 13 except that the raw materials for a coloring ink layer were changed as described above.

Preparation Example 18 - Thermal transfer ribbon 6

55 The raw materials for an adhesive layer and their amounts were as shown below.

- Adhesive layer -	
5	α -Olefin/maleic anhydride/butyl methacrylate copolymer resin (molar ratio = 1/1/1, Mw = 50,000)
Toluene	10 parts
Methyl ethyl ketone	45 parts
	40 parts

10 A coating solution for an adhesive layer, obtained from the above raw materials, was applied to the coloring ink layer of the same thermal transfer ribbon 1 as that obtained in Preparation Example 13 by a gravure coating method to form an adhesive layer having a dry coating thickness of 0.5 μ m, whereby a thermal transfer ribbon 6 was obtained.

15 **Preparation Example 19 - Thermal transfer ribbon 7**

The raw materials for a coloring ink layer and their amounts were as shown below.

- Coloring ink layer -	
20	Terpene resin (POLYSTAR T-100, supplied by Yasuhara Yushi Kogyo Co., Ltd.)
Carnauba wax	5 parts
Carbon black	12 parts
25 Dispersant	3 parts
Toluene	0.1 part
	80 parts

30 A thermal transfer ribbon 7 was obtained in the same manner as in Preparation Example 13 except that the raw materials for a coloring ink layer were changed as described above.

Preparation Example 20 - Thermal transfer ribbon 8

The raw materials for a heat-melting ink layer and their amounts were as shown below.

- Heat-melting ink layer -	
35	Ethylene-vinyl acetate copolymer resin (EVAFLEX V577-2, supplied by Du Pont-Mitsui Polychemicals Co., Ltd.)
40 Carbon black	8 parts
Dispersant	20 parts
Carnauba wax	2 parts
45 Paraffin wax (melting point 155°F)	60 parts
	10 parts

50 The above raw materials for a heat-melting ink layer were melted, fully dispersed and mixed under heat with a three-roll mill to give a heat-melting ink composition. This composition was applied to one surface of a 4.5 μ m thick polyethylene terephthalate film whose other surface had been coated with a heat-resistant back coating by a hot melt coating method to form a heat-melting ink layer having a thickness of 4 μ m, whereby a thermal transfer ribbon 8 was obtained.

Thermal transfer recording method

55 The thermal transfer recording was carried out using various combinations of the marking films and thermal transfer ribbons by means of a thermal transfer copying machine (Parette EC-10, supplied by Fuji Xerox Co., Ltd.).

Examples

The marking films and thermal transfer ribbons were combined as follows.

5	Examples	Marking film	Thermal transfer ribbon
10	1	F	1
	2	G	3
15	3	B	1
	4	A	4
	5	D	1
20	6	C	2
	7	E	4
	8	H	5
25	9	I	1
	10	J	2
	11	K	3
	12	G	6

Comparative Examples

The marking films and the thermal transfer ribbons were combined as follows.

30	Comparative Examples	Marking film	Thermal transfer ribbon
35	1	L	6
	2	L	7
40	3	L	1
	4	C	7
	5	E	8

The marking films to which characters or patterns were thermal-transferred in Examples and Comparative Examples were evaluated for outdoor weatherability, abrasion resistance, scratch resistance, adhesion and peelability of marking film as follows.

- 45 * Outdoor weatherability

A marking film to which a character or pattern was thermal-transferred ("recorded marking film" hereinafter) was set at an outdoor exposure tester positioned toward south at an angle of 45° from a horizontal line, and allowed to stand for 6 months.
- 50 * Abrasion resistance

A recorded portion was evaluated by a coloring fastness to rubbing test (JIS L-0823).
- * Scratch resistance

A recorded portion was evaluated by a pencil hardness test (JIS K-5401).
- * Adhesion

55 A cellophane tape (18 mm width Cellotape, supplied by Nichiban Ltd.) was attached to a recorded portion and forcibly peeled. The peeling degree of a recorded portion was evaluated.
- * Peelability of marking film

A recorded marking film was attached to a smooth surface of a stainless steel sheet and bonded

thereto with a 2 kg roller. Then, the stainless steel sheet with the recorded marking film attached thereto was allowed to stand in an environment having a temperature of 65°C and RH of 80 % for 168 hours, and then allowed to stand in an environment having a temperature of 23°C and RH of 65 % for 24 hours. The recorded marking film was peeled off from the stainless steel sheet, and the re-releasability was evaluated by observing whether or not there was a residual adhesive on the stainless steel sheet. Table 1 shows the results.

Table 1

10

	Resolution	Outdoor weather-ability	Abrasion resistance	Scratch resistance	Adhesion	Peel-ability
15	Ex. 1	A	A	A	A	A
	Ex. 2	A	A	A	A	A
	Ex. 3	A	A	AB	AB	AB
	Ex. 4	A	AB	AB	AB	X
20	Ex. 5	A	AB	AB	AB	-
	Ex. 6	A	A	AB	AB	A
	Ex. 7	A	AB	A	A	A
	Ex. 8	B	A	A	A	-
25	Ex. 9	A	AB	A	A	A
	Ex. 10	A	A	A	A	X
	Ex. 11	A	AB	A	A	-
	Ex. 12	A	A	A	A	-
30	CEx. 1	A	A	BX	X	X
	CEx. 2	A	A	X	X	X
	CEx. 3	A	A	AB	AB	X
	CEx. 4	A	A	B	B	A
35	CEx. 5	A	AB	X	B	A

Notes: Ex. = Example, CEx. = Comparative Example

A = Excellent, B = Good, X = Poor

40

Claims

1. A thermal transfer recording method which comprises thermally transferring an image onto a marking film from a thermal transfer ribbon, wherein the marking film is a plastic film containing a heat adhesive resin or is a plastic film on which a heat-sensitive image-receiving layer composed mainly of a heat adhesive resin is formed and the thermal transfer ribbon is a laminate comprising a substrate and, in order on one surface of the substrate, a separable layer and a coloring ink layer consisting essentially of a resin and coloring material.
2. A method according to claim 1, wherein the heat adhesive resin has a glass transition temperature of -30 to 80°C.
3. A method according to claim 1 or 2, wherein the heat adhesive resin has a softening or melting point of 40 to 180°C.
4. A method according to any one of the preceding claims wherein the plastic film is formed of at least one resin selected from a polyvinyl chloride resin, a urethane resin and a polyester resin.

5. A method according to any one of the preceding claims wherein the heat adhesive resin contains a poly-caprolactone of the formula $-(CH_2CH_2CH_2CH_2CH_2COO)_n-$.
6. A method according to any one of claims 1 to 4 wherein the heat adhesive resin contains a sucrose ester.
- 5 7. A method according to any one of the preceding claims wherein the coloring ink layer contains a sucrose ester as the resin.
- 10 8. A method according to any one of the preceding claims wherein the surface of the marking film to which the image is not transferred is provided with a releasable layer through an adhesive layer.
9. A method according to claim 8, wherein the adhesive layer has an adhesion strength of 50 to 1,000 gr/25 mm width when measured according to JIS-Z0237 adhesive tape/adhesive sheet test method.
- 15 10. A method according to any one of the preceding claims wherein the thermal transfer ribbon is a laminate comprising a substrate and, in order on the substrate, a separable layer, a coloring ink layer and an adhesive layer.
- 20 11. A method according to claim 10, wherein the adhesive layer contains a resin obtained by copolymerizing at least one compound selected from an α -olefin having at least 6 carbon atoms, maleic anhydride and (meth)acrylate.

25

30

35

40

45

50

55



Europäisches Patentamt
European Patent Office
Office européen des brevets



11) Publication number: 0 583 940 A3

12)

EUROPEAN PATENT APPLICATION

21) Application number: 93306340.6

51) Int. Cl.⁵: B41M 5/38, B41M 5/00,
B41M 5/40

22) Date of filing: 11.08.93

30) Priority: 14.08.92 JP 239018/92
05.03.93 JP 44799/93
05.03.93 JP 44800/93
12.03.93 JP 52343/93

43) Date of publication of application:
23.02.94 Bulletin 94/08

84) Designated Contracting States:
DE FR GB

88) Date of deferred publication of search report:
29.03.95 Bulletin 95/13

71) Applicant: TOYO INK MANUFACTURING CO.,
LTD.
3-13, Kyobashi 2-chome
Chuo-ku, Tokyo 104 (JP)

72) Inventor: Kimura, Yasunori, c/o Toyo Ink Mfg.
Co., Ltd.
3-13, Kyobashi,
2-chome
Chuo-ku, Tokyo (JP)

Inventor: Yoshikawa, Takeshi, c/o Toyo Ink
Mfg. Co., Ltd.
3-13, Kyobashi,
2-chome

Chuo-ku, Tokyo (JP)
Inventor: Kuwabara, Akifumi, c/o Toyo Ink
Mfg. Co., Ltd.

3-13, Kyobashi,
2-chome
Chuo-ku, Tokyo (JP)

Inventor: Nakao, Tatsuya, c/o Toyo Ink Mfg.
Co., Ltd.
3-13, Kyobashi,
2-chome

Chuo-ku, Tokyo (JP)
Inventor: Kashioka, Motohiko, c/o Toyo Ink
Mfg. Co., Ltd.

3-13, Kyobashi,
2-chome
Chuo-ku, Tokyo (JP)

Inventor: Ohmura, Toru c/o Toyo Ink Mfg. Co.,
Ltd.
3-13, Kyobashi,
2-chome
Chuo-ku, Tokyo (JP)

74) Representative: Myerscough, Philip Boyd
J.A. KEMP & CO.
14 South Square
Gray's Inn
London WC1R 5LX (GB)

54) Method of thermal transfer recording.

57) A thermal transfer recording method which comprises thermally transferring an image onto a marking film from a thermal transfer ribbon, wherein the marking film is a plastic film containing a heat adhesive resin or is a plastic film on which a heat-sensitive image-receiving layer composed mainly of a heat adhesive resin is formed and the thermal transfer ribbon is a laminate comprising a substrate and, in order on one surface of the substrate, a separable layer and a coloring ink layer consisting essentially of a resin and coloring material. The method permits the facile formation of fine or complicated, multi-color images on a marking film in quick operation at a low cost, and can give a recorded marking film having excellent weatherability, abrasion resistance and scratch resistance.

EP 0 583 940 A3

Jouve, 18, rue Saint-Denis, 75001 PARIS



EUROPEAN SEARCH REPORT

Application Number
EP 93 30 6340

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int.Cl.5)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
X	EP-A-0 367 149 (DAI NIPPON PRINTING COMPANY LIMITED) * page 5, line 12 - line 19 * * page 5, line 45 - line 50 * * claims 1,4,13; examples 1-5 * -----	1-11	B41M5/38 B41M5/00 B41M5/40
A	EP-A-0 228 066 (EASTMAN KODAK COMPANY) * page 2, line 11 - line 18; claims 1-3 * -----	1-11	
			TECHNICAL FIELDS SEARCHED (Int.Cl.5)
			B41M
The present search report has been drawn up for all claims			
Place of search	Date of completion of the search		Examiner
THE HAGUE	13 January 1995		Bacon, A
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons A : member of the same patent family, corresponding document	